



Technical Data Sheet

XL20/40-100/205-6FT-UAC, XP20/40-625-6FT-UAC, XF30-65/100-6FT-PSS

Product Description

dasso.XTR Lumber is solid and high density decking board, made from compressed bamboo fibers with a special, patented heat treatment process, making it one of the strongest, hardest and most durable materials on the market to create the perfect space for outdoor entertainment and relaxation. Like any untreated tropical hardwood species, when exposed to outdoor conditions, dasso.XTR Lumber will turn grey over time creating a very natural look.

Product Technical Specification and Tolerance

Properties	Standard
Dimension and Tolerance	dimension: 1860mm x205mm x 20mm 1860mm x152mm x 40mm 1860mm x625mm x 20/40mm 1860mm x65/100mm x 30mm length tolerance: $\pm 0.5\text{mm}$ width tolerance: $\pm 0.15\text{mm}$ thickness tolerance: $\pm 0.15\text{mm}$
Density/Specific Gravity	1.15 g/cm ³
Moisture content	10-14%
Hardness	106.8N/mm ² (DIN EN 1534)
Static Bending Strength	74.4N/mm ² (DIN EN 408)
Modulus of Elasticity	19100N/mm ² (DIN EN 408)
Termite Resistance Level	DC M (EN117)
Biological Durability	class 1 (EN 350:2016)
Release of Formaldehyde	E1(0.1mg/m ² h) (GB/T17657-2013)
Thickness of Swelling	5.1% (DIN EN 15534-1)
Rate	
Width of Swelling Rate	0.6% (DIN EN 15534-1)



Warping	≤ 6mm and quantity is less than 10%.
Banana Shape	≤ 1mm/m along the length of the panels
Bamboo Nodes	Nodus are separated its width ≤ 10 mm.
Height Difference	≤ 0.5mm
Packaging and label	According to packaging layout drawing, check the label

Storage

- The warehouse should be well ventilated, with relative humidity from 45 to 75% at temperatures ranging from 50°F (+10°C) to 104°F (+40°C).
- Do not store product in pest infested and/or unsuitable warehouse.
- Leave the products in its original package when not in use, cover the bundles from top and bottom to avoid the influence of climatic events and other environmental hazards.
- Store the product horizontally on the ground with pallet shoe on every pallet. The bottom pallet should be placed on an even footing on spacer-pads or palettes. The maximum height of stacked bundles should not exceed 4.5 m.
- The difference between the spacers should not be more than 600mm, with distance of starting and ending spacer from the edge of the bundle not exceeding 200mm (the number of spacers should not be less than 3).