Technical Data Sheet
(Ultra slippery resistance Decking)



Product code: XD20-SG1-5TG-PSR-S
Size: L1850*W137*T20
L1850*W137*T18

Product Description

dasso.XTR is solid and high density decking board, made from compressed bamboo fibers with a special, patented heat treatment process, making it one of the strongest, hardest and most durable materials on the market to create the perfect space for outdoor entertainment and relaxation. A unique feature of dasso.XTR is the head tongue and groove: this can only be done with very stable materials and enables connection of an unlimited number of boards in the length. Dasso Ultra slippery resistance decking offers a unique natural grooved design which is realized through Dasso-patented technology . This grooved design not only keeps the natural appearance, but also brings higher slippery ratings P4, so it is the perfect and safest choice among the natural materials for commercial and residential application like walkways, swimming pools or slopes which prevents from slipping in the wet.

Product Technical Specification and Tolerance

Properties	**Standard**
Tolerance	length tolerance: ±0.5mm width tolerance: ±0.2mm thickness tolerance: ±0.15mm T&G tolerance: ±0.1mm
Density/Specific Gravity	1.15 g/cm3
Moisture content	10-14%
Hardness	106.8N/mm²（DIN EN 1534）
Slip Resistance	P4（AS 4586）
Reaction to Fire	Bf1-s1 (DIN EN 13501-1:2010)
Static Bending Strength	74.4N/mm²（DIN EN 408）

Modulus of Elasticity	19100N/mm² （DIN EN 408）
Termite Resistance Level	DC M (EN117)
Biological Durability	Class 1（EN 350:2016）
Release of Formaldehyde	E1(0.1mg/m²h) (GB/T17657-2013)
Thickness of Swelling Rate	5.1% (DIN EN 15534-1)
Width of Swelling Rate	0.6% (DIN EN 15534-1)
Appearance	Anti-slip resistance Smooth surface is use as top surface Texture smooth Color greyish brown when unfinished and turn to rich dark brown after primed with penetrating oiled Natural grain and color may vary as this is a natural fiber product
Cupping	≤ 0.3 mm
Warping	≤ 6mm and quantity is less than 10%.
Banana Shape	≤ 1mm/m along the length of the panels
Bamboo Nodes	Nodes are separated its width ≤ 10 mm.
Height Difference	≤ 0.5mm
Tool Marks	Minor
T&G	Waxed, dimension as shown in technical drawing
Finishes	Woca fully cured, uniform with no excess
Thickness Swelling Rate of Water Absorption Test	≤ 3%, no obvious cracking in cross cut end in 100°C hot water for 1 hour
Packaging and label	According to packaging layout drawing, check the label

Storage

- The warehouse should be well ventilated, with relative humidity from 45 to 75%at temperatures ranging from 50°F (+10°C) to 104°F (+40°C).
- Do not store product in pest infested and/or unsuitable warehouse.
- Leave the products in its original package when not in use, cover the bundles from top and bottom to avoid the influence of climatic events and other environmental hazards.
- Store the product horizontally on the ground with pallet shoe on every pallet. The bottom pallet should be placed on an even footing on spacer-pads or palettes. The maximum height of stacked bundles should not exceed 4.5 m.
- The difference between the spacers should not be more than 600m, with distance of starting and ending spacer from the edge of the bundle not exceeding 200mm (the number ofspacers should not be less than 3).